

JC07 Rec'd PCT/PTO 22 JAN 2002

FORM PTO-1390 U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER 19789-8
<b>TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US) CONCERNING A FILING UNDER 35 U.S.C. 371</b>		U.S. APPLIC. NO. (if known, see 37 CFR 1.5) <b>10/031731</b>
		PRIORITY DATE CLAIMED July 19, 1999 et al.
INTERNATIONAL APPLICATION NO. PCT/US00/19646	INTERNATIONAL FILING DATE July 19, 2000	
TITLE OF INVENTION Acyloxy Silane Treatments for Metals		
APPLICANT(S) FOR DO/EO/US VAN OOIJ et al.		
<p>Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:</p> <ol style="list-style-type: none"> <li><input checked="" type="checkbox"/> This is a <b>FIRST</b> submission of items concerning a filing under 35 U.S.C. 371.</li> <li><input type="checkbox"/> This is a <b>SECOND</b> or <b>SUBSEQUENT</b> submission of items concerning a filing under 35 U.S.C. 371.</li> <li><input checked="" type="checkbox"/> This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).</li> <li><input checked="" type="checkbox"/> A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.</li> <li><input type="checkbox"/> A copy of the International Application as filed (35 U.S.C. 371(c)(2))             <ol style="list-style-type: none"> <li><input type="checkbox"/> is transmitted herewith (required only if not transmitted by the International Bureau).</li> <li><input checked="" type="checkbox"/> has been transmitted by the International Bureau.</li> <li><input type="checkbox"/> is not required, as the application was filed in the United States Receiving Office (RO/US)</li> </ol> </li> <li><input type="checkbox"/> A translation of the International Application into English (35 U.S.C. 371(c)(2)).</li> <li><input type="checkbox"/> Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))             <ol style="list-style-type: none"> <li><input type="checkbox"/> are transmitted herewith (required only if not transmitted by the International Bureau).</li> <li><input type="checkbox"/> have been transmitted by the International Bureau.</li> <li><input type="checkbox"/> have not been made; however, the time limit for making such amendment has NOT expired.</li> <li><input checked="" type="checkbox"/> have not been made and will not be made.</li> </ol> </li> <li><input type="checkbox"/> A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).</li> <li><input type="checkbox"/> An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).</li> <li><input type="checkbox"/> A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).</li> </ol> <p><b>Items 11. to 16. below concern other document(s) or information included:</b></p> <ol style="list-style-type: none"> <li><input type="checkbox"/> An Information Disclosure Statement under 37 CFR 1.97 and 1.98.</li> <li><input type="checkbox"/> An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.</li> <li><input checked="" type="checkbox"/> A FIRST preliminary amendment. <input type="checkbox"/> A SECOND or SUBSEQUENT preliminary amendment.</li> <li><input type="checkbox"/> A substitute specification.</li> <li><input type="checkbox"/> A change of power of attorney and/or address letter.</li> <li><input checked="" type="checkbox"/> Other items or information.: Return Postcard</li> </ol>		


**CERTIFICATE OF MAILING**

"Express Mail" mailing label #EV051446239US:


Date of Deposit: January 22, 2002

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to: Box PCT; Assistant Commissioner for Patents; Washington, DC 20231.

Martin J. Miller



JC13 Rec'd PCT/PTO 22 JAN 2002

U.S. APPLIC. NO. (if known, see 37 CFR 1.50) <b>10/031731</b>		INTERNATIONAL APPLICATION NO. PCT/US00/19646		ATTORNEY'S DOCKET NUMBER 19789-8	
				CALCULATIONS	PTO USE ONLY
17. The following fees are submitted:					
<b>Basic National Fee (37 CFR 1.492(a)(1)-(5)):</b> <input checked="" type="checkbox"/> Search Report has been prepared by the EPO or JPO \$890.00				890.00	
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) \$710.00					
<input type="checkbox"/> No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee paid to USPTO (37 CFR 1.445(a)(2)) \$740.00					
<input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$1040.00					
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00					
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$ 890.00	
Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).				\$	
Claims	Number Filed	Number Extra	Rate		
Total Claims	29	9	x \$18.00	\$ 162.00	
Independent Claims	3	0	x \$84.00	\$ ---	
Multiple dependent claim(s) (if applicable)			+ \$280.00	\$ ---	
TOTAL OF ABOVE CALCULATIONS =				\$ 1,052.00	
<input type="checkbox"/> Applicant(s) claim(s) small entity status, 37 C.F.R. 1.27. The fees indicated above are reduced by 1/2.				\$	
SUBTOTAL =				\$ 1,052.00	
Processing fee of \$130.00 for furnishing the English translation later than the <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				+	\$
TOTAL NATIONAL FEE =				\$ 1,052.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				+	\$
TOTAL FEES ENCLOSED =				<u>1,052.00</u> \$	
				Amount to be refunded	\$
				Amount to be charged	\$
a. <input type="checkbox"/> A check in the amount of \$ to cover the above fees is enclosed. b. <input checked="" type="checkbox"/> Please charge my Deposit Account No. 04-1133 in the amount of \$1,052.00 to cover the above fees. A duplicate copy of this sheet is enclosed. c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 04-1133.					
<b>NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.</b>					
<input checked="" type="checkbox"/> CUSTOMER NO. 24256		OR		DINSMORE & SHOHL 1900 Chemed Center 255 East Fifth Street Cincinnati, Ohio 45202 (513) 977-8200	
 SIGNATURE		35,953		REGISTRATION NUMBER	
Martin J. Miller				DATE <u>January 22, 2002</u>	
TYPED OR PRINTED NAME					

Docket No. 19789-8


PATENT

**CERTIFICATE OF EXPRESS MAILING**

Express Mail" mailing label: EV 051446 239 US

Date of Deposit: January 22, 2002

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to: Box PCT; Assistant Commissioner for Patents; Washington, D.C. 20231.

  
Martin J. Miller

**IN THE UNITED STATES PATENT & TRADEMARK OFFICE**

In re National Stage Application for PCT/US00/19646

Applicant: van Ooij et al. : Paper No.:

Filing Date: January 22, 2001 :

For: **ACYLOXY SILANE TREATMENTS METALS**

**PRELIMINARY AMENDMENT**

BOX PCT  
Assistant Commissioner for Patents  
Washington, DC 20231

Dear Sir:

Prior to examination of this application, please amend this application as follows:

In the claims:

Please amend claim 4 as follows:

4. (amended) The method according to claim 1, wherein the acyloxy silane comprises a single tetrasubstituted silicon atom, wherein the substituents are individually selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, alkaryl, aralkyl, vinyl, amino, ureido, glycidoxo, epoxy, hydroxy, alkoxy, aryloxy and acyloxy,


or any of the group alkyl, alkenyl, alkynyl, aryl, alkaryl and aralkyl substituted by a group selected from the group consisting of vinyl, amine, ureido, glycidoxy, epoxy, hydroxy and alkoxy, with the proviso that at least one of the substituents on the silicon atom is an acyloxy group

Please amend claim 5 as follows:

5. (amended) The method according to claim 1, wherein the acyloxy groups are preferably all the same and are selected from the group consisting of C<sub>2-12</sub> alkanoyloxy, C<sub>3-12</sub> alkenoyloxy, C<sub>3-12</sub> alkynoyloxy and C<sub>7-18</sub> arenoyloxy, preferably C<sub>2-6</sub> alkanoyloxy, C<sub>3-6</sub> alkenoyloxy, C<sub>3-6</sub> alkynoyloxy and C<sub>7-12</sub> arenoyloxy, preferably ethanoyloxy or methanoyloxy groups.

Please amend claim 6 as follows:


6. (amended) The method according to claim 1, wherein the acyloxy silane is selected from the group



wherein W, X, Y and Z are selected from the group consisting of a C-Si bond, substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups and unsubstituted aromatic groups; and R is selected from methyl, ethyl and propyl, preferably ethyl.

Please amend claim 9 as follows:

9. (amended) The method according to claim 7, wherein the acyloxysilane has the structure




**SECRET**


Please amend claim 13 as follows:

Please amend claim 14 as follows:

$$\begin{array}{c} R^3 \\ \diagdown \\ N - X' - Si - OR^2 \\ \diagup \\ R^3 \end{array} \begin{array}{c} OR^2 \\ | \\ Si - OR^2 \\ | \\ OR^2 \end{array}$$

R<sup>3</sup> is a group individually selected from the group consisting of hydrogen, C<sub>1</sub>-C<sub>6</sub> alkyl, C<sub>2</sub>-C<sub>6</sub> alkenyl, C<sub>1</sub>-C<sub>6</sub> alkyl substituted with at least one amino group, C<sub>2</sub>-C<sub>6</sub> alkenyl substituted with at least one amino group, arylene and alkylarylene.


16. (amended) The method of claim 13, wherein the basic compound is a bis-silyl aminosilane(s) having the structure 



wherein  $R^4$  is individually selected from the group consisting of: hydrogen and  $C_1$ - $C_{24}$  alkyl;

$R^5$  is individually selected from the group consisting of: substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups, and unsubstituted aromatic groups; and

$-X^2$  is either:



wherein each  $R^6$  is individually selected from the group consisting of: hydrogen, substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups; and

$R^7$  is selected from the group consisting of: substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups.

Please amend claim 18 as follows:

18. (amended) The method according to claim 1, wherein a polymer coating is applied to the treated metal substrate.

Please amend claim 20 as follows:

20. (amended) The method according to claim 1, wherein the solution contains at least about 0.1% acyloxy silanes by volume, more preferably at least about 1% acyloxy silanes by volume, most preferably between about 2% and about 5% by volume.

Please amend claim 21 as follows:

21. (amended) The method according to claim 1, wherein the solution contains at least about 0.1% basic compound by volume, more preferably at least about 1% by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

Please amend claim 22 as follows:

22. (amended) A composition comprising at least one acyloxy silane which comprises at least one acyloxy group, and at least one basic compound, wherein the solution pH is between 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 and wherein the solution is substantially free of acids other than acids produced upon hydrolysis of the acyloxy silanes.

Please amend claim 24 as follows:

24. (amended) The composition according to claim 22, wherein the solution contains at least about 0.1% basic compound by volume, more preferably at least about 1% by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

Please amend claim 25 as follows:

25. (amended) A composition comprising at least one acyloxy silane which comprises at least one acyloxy group, and at least one basic compound, wherein the acyloxy silane is substantially unhydrolysed and the composition is substantially free of water.

Please amend claim 28 as follows:

28. (amended) The composition according to claim 22, comprising additional components selected from stabilisers, pigments, anti-oxidants, desiccants, adhesion promoters, corrosion inhibitors and mixtures thereof.

Please cancel claim 29.

Please add the following new claim:

30. The composition according to claim 25, comprising additional components selected from stabilisers, pigments, anti-oxidants, desiccants, adhesion promoters, corrosion inhibitors and mixtures thereof.

**SECRET**

Respectfully submitted,

Martin J. Miller, Reg. No. 35,953  
Dinsmore & Shohl LLP  
1900 Chemed Center  
255 East Fifth Street  
Cincinnati, Ohio 45202  
(513) 977-8565



Claim 4 has been amended as follows:


4. (amended) The method according to [any preceding] claim 1, wherein the [acyloxysilane] acyloxy silane comprises a single tetrasubstituted silicon atom, wherein the substituents are individually selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, alkaryl, aralkyl, vinyl, amino, ureido, glycidoxy, epoxy, hydroxy, alkoxy, aryloxy and acyloxy, or any of the group alkyl, alkenyl, alkynyl, aryl, alkaryl and aralkyl substituted by a group selected from the group consisting of vinyl, amine, ureido, glycidoxy, epoxy, hydroxy and alkoxy, with the proviso that at least one of the substituents on the silicon atom is an acyloxy group

Claim 5 has been amended as follows:

5. (amended) The method according to [any preceding] claim 1, wherein the acyloxy groups are preferably all the same and are selected from the group consisting of C<sub>2-12</sub> alkanoyloxy, C<sub>3-12</sub> alkenoyloxy, C<sub>3-12</sub> alkynoyloxy and C<sub>7-18</sub> arenoyloxy, preferably C<sub>2-6</sub> alkanoyloxy, C<sub>3-6</sub> alkenoyloxy, C<sub>3-6</sub> alkynoyloxy and C<sub>7-12</sub> arenoyloxy, preferably ethanoyloxy or methanoyloxy groups.

Claim 6 has been amended as follows:


6. (amended) The method according to [any preceding] claim 1, wherein the acyloxy silane is selected from the group



wherein W, X, Y and Z are selected from the group consisting of a C-Si bond, substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups and unsubstituted aromatic groups; and  
R is selected from methyl, ethyl and propyl, preferably ethyl.

Claim 9 has been amended as follows:

9. (amended) The method according to claim 7 [or 8], wherein the acyloxysilane has the structure



wherein Q is selected from the group consisting of either a bond, an aliphatic or aromatic group; and


R<sup>1</sup> is selected from methyl, ethyl and propyl.

Claim 13 has been amended as follows:

13. (amended) The method according to [any preceding] claim 1, wherein the basic compound is selected from the carbonates, hydrogen carbonates and hydroxides of the alkali and alkaline earth metals, organic amines, ammonia, amides and silanes, and mixtures thereof.

Claim 14 has been amended as follows:

14. (amended) The method according to [any preceding] claim 13, wherein the basic compound is a basic silane compound selected from compounds having the general structure




wherein R<sup>2</sup> is chosen from the group consisting of hydrogen and C<sub>1</sub>-C<sub>24</sub> alkyl, preferably C<sub>1</sub>-C<sub>6</sub> alkyl and each R may be the same or different:

X<sup>1</sup> is selected from the group consisting of a bond, a substituted or unsubstituted aliphatic or aromatic group; and

R<sup>3</sup> is a group individually selected from the group consisting of hydrogen, C<sub>1</sub>-C<sub>6</sub>

1 2 3 4 5 6 7 8 9 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48 49 50 51 52 53 54 55 56 57 58 59 60 61 62 63 64 65 66 67 68 69 70 71 72 73 74 75 76 77 78 79 80 81 82 83 84 85 86 87 88 89 90 91 92 93 94 95 96 97 98 99 100  
 101 102 103 104 105 106 107 108 109 110 111 112 113 114 115 116 117 118 119 120 121 122 123 124 125 126 127 128 129 130 131 132 133 134 135 136 137 138 139 140 141 142 143 144 145 146 147 148 149 150 151 152 153 154 155 156 157 158 159 160 161 162 163 164 165 166 167 168 169 170 171 172 173 174 175 176 177 178 179 180 181 182 183 184 185 186 187 188 189 190 191 192 193 194 195 196 197 198 199 200  
 201 202 203 204 205 206 207 208 209 210 211 212 213 214 215 216 217 218 219 220 221 222 223 224 225 226 227 228 229 230 231 232 233 234 235 236 237 238 239 240 241 242 243 244 245 246 247 248 249 250 251 252 253 254 255 256 257 258 259 260 261 262 263 264 265 266 267 268 269 270 271 272 273 274 275 276 277 278 279 280 281 282 283 284 285 286 287 288 289 290 291 292 293 294 295 296 297 298 299 300  
 301 302 303 304 305 306 307 308 309 310 311 312 313 314 315 316 317 318 319 320 321 322 323 324 325 326 327 328 329 330 331 332 333 334 335 336 337 338 339 340 341 342 343 344 345 346 347 348 349 350 351 352 353 354 355 356 357 358 359 360 361 362 363 364 365 366 367 368 369 370 371 372 373 374 375 376 377 378 379 380 381 382 383 384 385 386 387 388 389 390 391 392 393 394 395 396 397 398 399 400  
 401 402 403 404 405 406 407 408 409 410 411 412 413 414 415 416 417 418 419 420 421 422 423 424 425 426 427 428 429 430 431 432 433 434 435 436 437 438 439 440 441 442 443 444 445 446 447 448 449 450 451 452 453 454 455 456 457 458 459 460 461 462 463 464 465 466 467 468 469 470 471 472 473 474 475 476 477 478 479 480 481 482 483 484 485 486 487 488 489 490 491 492 493 494 495 496 497 498 499 500  
 501 502 503 504 505 506 507 508 509 510 511 512 513 514 515 516 517 518 519 520 521 522 523 524 525 526 527 528 529 530 531 532 533 534 535 536 537 538 539 540 541 542 543 544 545 546 547 548 549 550 551 552 553 554 555 556 557 558 559 560 561 562 563 564 565 566 567 568 569 570 571 572 573 574 575 576 577 578 579 580 581 582 583 584 585 586 587 588 589 590 591 592 593 594 595 596 597 598 599 600  
 601 602 603 604 605 606 607 608 609 610 611 612 613 614 615 616 617 618 619 620 621 622 623 624 625 626 627 628 629 630 631 632 633 634 635 636 637 638 639 640 641 642 643 644 645 646 647 648 649 650 651 652 653 654 655 656 657 658 659 660 661 662 663 664 665 666 667 668 669 670 671 672 673 674 675 676 677 678 679 680 681 682 683 684 685 686 687 688 689 690 691 692 693 694 695 696 697 698 699 700  
 701 702 703 704 705 706 707 708 709 710 711 712 713 714 715 716 717 718 719 720 721 722 723 724 725 726 727 728 729 730 731 732 733 734 735 736 737 738 739 740 741 742 743 744 745 746 747 748 749 750 751 752 753 754 755 756 757 758 759 760 761 762 763 764 765 766 767 768 769 770 771 772 773 774 775 776 777 778 779 780 781 782 783 784 785 786 787 788 789 790 791 792 793 794 795 796 797 798 799 800  
 801 802 803 804 805 806 807 808 809 810 811 812 813 814 815 816 817 818 819 820 821 822 823 824 825 826 827 828 829 830 831 832 833 834 835 836 837 838 839 840 841 842 843 844 845 846 847 848 849 850 851 852 853 854 855 856 857 858 859 860 861 862 863 864 865 866 867 868 869 870 871 872 873 874 875 876 877 878 879 880 881 882 883 884 885 886 887 888 889 890 891 892 893 894 895 896 897 898 899 900  
 901 902 903 904 905 906 907 908 909 910 911 912 913 914 915 916 917 918 919 920 921 922 923 924 925 926 927 928 929 930 931 932 933 934 935 936 937 938 939 940 941 942 943 944 945 946 947 948 949 950 951 952 953 954 955 956 957 958 959 960 961 962 963 964 965 966 967 968 969 970 971 972 973 974 975 976 977 978 979 980 981 982 983 984 985 986 987 988 989 990 991 992 993 994 995 996 997 998 999 1000  
 1001 1002 1003 1004 1005 1006 1007 1008 1009 1010 1011 1012 1013 1014 1015 1016 1017 1018 1019 1020 1021 1022 1023 1024 1025 1026 1027 1028 1029 1030 1031 103

16. (amended) The method of [any of claims 1 to] claim 13, wherein the basic compound is a bis-silyl aminosilane(s) having the structure



R<sup>5</sup> is individually selected from the group consisting of: substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups, and unsubstituted aromatic groups; and

$$\begin{array}{c} R^6 \\ | \\ -N- \end{array} \quad \text{or} \quad \begin{array}{c} R^6 \qquad R^6 \\ | \qquad \qquad | \\ -N- R^7 - N- \end{array}$$

R<sup>7</sup> is selected from the group consisting of: substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups.

18. (amended) The method according to [any preceding] claim 1, wherein a polymer coating is applied to the treated metal substrate.

20. (amended) The method according to [any preceding] claim 1, wherein the solution contains at least about 0.1% acyloxy silanes by volume, more preferably at least about 1% acyloxy silanes by volume, most preferably between about 2% and

about 5% by volume.

Claim 21 has been amended as follows:

21. (amended) The method according to [any preceding] claim 1, wherein the solution contains at least about 0.1% basic compound by volume, more preferably at least about 1% by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

Claim 22 has been amended as follows:

22. (amended) A composition comprising [an] at least one acyloxy silane which comprises at least one acyloxy group, and [a] at least one basic compound [as defined in any preceding claim], wherein the solution pH is between 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 and wherein the solution is substantially free of acids other than acids produced upon hydrolysis of the acyloxy silanes.

Claim 24 has been amended as follows:

24. (amended) The composition according to claim 22 [or 23], wherein the solution contains at least about 0.1% basic compound by volume, more preferably at least about 1% by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

Claim 25 has been amended as follows:

25. (amended) A composition comprising [an] at least one acyloxy silane which comprises at least one acyloxy group, and [a] at least one basic compound [as defined in any of claims 1 to 22], wherein the acyloxy silane is substantially unhydrolysed and the composition is substantially free of water.

Claim 28 has been amended as follows:

28. (amended) The composition according to [any of claims] claim 22 [to 27], comprising additional components selected from stabilisers, pigments, anti-oxidants, desiccants, adhesion promoters, corrosion inhibitors and mixtures thereof.

Claim 29 has been canceled.

The following new claim has been added:

30. The composition according to claim 25, comprising additional components selected from stabilisers, pigments, anti-oxidants, desiccants, adhesion promoters, corrosion inhibitors and mixtures thereof.

**ACYLOXY SILANE TREATMENTS FOR METALS****Background of the Invention****Field of the Invention**

5           The present invention relates to silane coatings for metals. More particularly, the present invention provides coatings which include an acyloxy silane, and are particularly useful for preventing corrosion and/or promoting  
10          adhesion between a metal substrate and a polymer layer applied to the treated metal substrate. Solutions for applying such coatings, compositions as well as methods of treating metal surfaces, are also provided.

**Description of Related Art**

15           Most metals are susceptible to corrosion, including the formation of various types of rust. Such corrosion will significantly affect the quality of such metals, as well as that of the products produced therefrom. Although rust and the like may often be removed, such steps are costly and may further diminish the strength of the metal. In addition, when polymer coatings such as paints, adhesives or rubbers are applied to the metals, corrosion may cause a loss of  
20          adhesion between the polymer coating and the metal.

          By way of example, metallic coated steel sheet such as galvanized steel is used in many industries, including the automotive, construction and appliance industries. In most cases, the galvanized steel is painted or otherwise coated with a polymer layer to achieve a durable and aesthetically-pleasing product.  
25          Galvanized steel, particularly hot-dipped galvanized steel, however, often develops "white rust" during storage and shipment.

          White rust (also called "wet-storage stain") is typically caused by moisture condensation on the surface of galvanized steel which reacts with the zinc coating. On products such as GALVALUME®, the wet-storage stain is black in  
30          color ("black rust"). White rust (as well as black rust) is aesthetically unappealing and impairs the ability of the galvanized steel to be painted or

otherwise coated with a polymer. Thus, prior to such coating, the surface of the galvanized steel must be pretreated in order to remove the white rust and prevent its reformation beneath the polymer layer. Various methods are currently employed to not only prevent the formation of white rust during shipment and storage, but also to prevent the formation of white rust beneath a polymer coating (e.g., paint).

In order to prevent white rust on hot-dipped galvanized steel during storage and shipping, the surface of the steel is often passivated by forming a thin chromate film on the surface of the steel. While such chromate coatings do provide resistance to the formation of white rust, chromium is highly toxic and environmentally undesirable. It is also known to employ a phosphate conversion coating in conjunction with a chromate rinse in order to improve paint adherence and provide corrosion protection. It is believed that the chromate rinse covers the pores in the phosphate coating, thereby improving the corrosion resistance and adhesion performance. Once again, however, it is highly desirable to eliminate the use of chromate altogether. Unfortunately, however, the phosphate conversion coating is generally not very effective without the chromate rinse.

Recently, various techniques for eliminating the use of chromate have been proposed. These include coating the galvanized steel with an inorganic silicate followed by treating the silicate coating with an organofunctional silane (U.S. Patent No. 5,108,793).

U.S. Patent No. 5,292,549 teaches the rinsing of metallic coated steel sheet with a solution containing an organofunctional silane and a crosslinking agent.

U.S. Patent No. 6,071,566 relates to a method of treating a metal substrate to provide permanent corrosion resistance. The method comprises applying a solution containing one or more vinyl silanes in admixture with one or more multi-silyl-functional silanes to a metal substrate in order to form a coating.

Various other techniques for preventing the formation of white rust on galvanized steel, as well as preventing corrosion on other types of metals, have also been proposed. Many of the proposed techniques described in the prior art are, however, ineffective, or require time-consuming, energy-inefficient, multi-step processes. Thus, there is a need for a simple, low-cost technique for preventing corrosion on the surface of metal.

A particular problem associated with the silane treatments of the prior art is the rate of hydrolysis of the silane compounds. Such compounds are generally hydrolysed in water, at a specific pH, prior to application of the solution to the substrate to be treated. The rate of hydrolysis varies between silanes, and the degree of hydrolysis is a priori not known. Generally, it has to be guessed when the solution is ready for application. When the solution has turned cloudy, this indicates that condensation of the silanes has occurred and the effectiveness of the treatment solution is reduced.

A further problem with the prior art techniques is the inherent insolubility in aqueous media of some of the silanes employed in the metal treatments. To overcome this problem it is commonplace to dissolve the silane with the aid of an organic solvent, for example, alcohols. Thus a final treatment solution commonly contains up to 60% alcohol. The use of many volatile organic compounds (VOCs), including solvents, is highly undesirable from an economic, as well as an environmental perspective. Apart from the cost of such organic solvents, including the cost of their disposal and methods of treatment solution preparation, such compounds present a threat to the environment and are a hazard to the premises and personnel handling the materials.

A further problem is that the silane systems used in treatment solutions have to have their pH maintained in specific ranges by the initial and continuous addition of acids or bases.

It would therefore be desirable to provide an effective treatment method for metal surfaces, especially to prevent corrosion, and/or improve adhesion.

It would also be desirable to provide a treatment solution useful in preventing corrosion, and/or adhesion promotion of metal surfaces, for example,



steel, aluminium, aluminium alloys, zinc, zinc alloys, magnesium, magnesium alloys, copper, copper alloys, tin and tin alloys, particularly zinc, zinc alloys, and other metals having a zinc-containing coating thereon

It would additionally be desirable to provide a metal surface having improved corrosion resistance and/or improved adhesion characteristics.

### **Summary of the Invention**

The present invention provides a method of treating a metal surface, comprising the steps of:

- (a) providing a metal substrate; and
- (b) applying a solution to said metal substrate, said solution comprising
  - (i) at least one acyloxy silane which comprises at least one acyloxy group, wherein said silane has been at least partially hydrolysed; and
  - (ii) at least one basic compound;

wherein the acyloxy silane and the basic compound are present in concentrations to provide a solution pH of between about 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 and wherein the solution is substantially free of acid other than acid produced upon hydrolysis of the acyloxy silane.

The present invention also provides a composition comprising at least one acyloxy silane and at least one basic compound, wherein the at least one acyloxy silane is at least partially hydrolyzed. A metal surface having improved corrosion resistance and/or adhesion and a composition concentrate is also provided.

### **Detailed Description of the Invention**


The acyloxy silane(s) utilised in the present invention may comprise one or more silyl groups and the solution may contain a mixture of acyloxy silanes

Where the acyloxy silane comprises a single silyl group the silicon atom is tetrasubstituted, wherein the substituents are individually selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, alkaryl, aralkyl, vinyl, amino, ureido, glycidoxy, epoxy, hydroxy, alkoxy, aryloxy and acyloxy, or any of the group alkyl, alkenyl, alkynyl, aryl, alkaryl and aralkyl substituted by a group selected from the group consisting of vinyl, amine, ureido, glycidoxy, epoxy, hydroxy and alkoxy, with the proviso that at least one of the substituents on the silicon atom is an acyloxy group.

Where more than one acyloxy group is attached to the silicon atom of the silyl group, the acyloxy groups are preferably all the same. The acyloxy group(s) are preferably selected from the group consisting of C<sub>2-12</sub> alkanoyloxy, C<sub>3-12</sub> alkenoyloxy, C<sub>3-12</sub> alkynoyloxy and C<sub>7-18</sub> arenoyloxy, preferably C<sub>2-6</sub> alkanoyloxy, C<sub>3-6</sub> alkenoyloxy, C<sub>3-6</sub> alkynoyloxy and C<sub>7-12</sub> arenoyloxy. Most preferably the acyloxy groups are all the same and are ethanoyloxy (acetoxy) or methanoyloxy groups.

Where the acyloxy silane comprises a single silyl group, preferably three of the substituents on the silyl group are acyloxy groups and the fourth substituent is preferably selected from a the group consisting of vinyl or vinyl substituted group, amine or amine substituted group, ureido or ureido substituted group and glycidoxy or glycidoxy substituted group.

In a particularly preferred embodiment, the acyloxy silane is selected from the group consisting of




wherein W, X, Y and Z are selected from the group consisting of a C-Si bond, substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups and unsubstituted aromatic groups; and

R is selected from methyl, ethyl and propyl, preferably ethyl.

The acyloxy silane may comprises more than one silyl group. Although the term acyloxy silane generically refers to such a compound, it may be referred to as a multi-silyl-acyloxy silane. More than one multi-silyl-acyloxy silane may be employed in a mixture with one or more other multi-silyl-acyloxy silanes or one or more acyloxy silanes containing a single silyl group as described above.

The acyloxy groups bound to the silicon atoms of the silyl groups of the multi-silyl-acyloxy silane are preferably all the same and are preferably selected from the group consisting of C<sub>2-12</sub> alkanoyloxy, C<sub>3-12</sub> alkenoyloxy, C<sub>3-12</sub> alkynoyloxy and C<sub>7-18</sub> arenoyloxy, preferably C<sub>2-8</sub> alkanoyloxy, C<sub>3-6</sub> alkenoyloxy, C<sub>3-6</sub> alkynoyloxy and C<sub>7-12</sub> arenoyloxy. Most preferably the acyloxy groups are all the same and are ethanoyloxy or methanoyloxy groups.

Preferably the multi-silyl-acyloxy silane utilised in the present invention has the structure



wherein Q is selected from the group consisting of either a bond, an aliphatic or aromatic group; and

R<sup>1</sup> is selected from methyl, ethyl and propyl.

Preferably Q is selected from the group consisting of a bond, C<sub>1</sub>-C<sub>6</sub> alkylene, C<sub>2</sub>-C<sub>6</sub> alkenylene, C<sub>1</sub>-C<sub>6</sub> alkylene substituted with at least one amino group, C<sub>2</sub>-C<sub>6</sub> alkenylene substituted with at least one amino group, C<sub>1</sub>-C<sub>6</sub> alkylene substituted with at least one sulfide group containing 1 to 6 sulfur atoms, C<sub>2</sub>-C<sub>6</sub> alkenylene substituted with at least one sulfide group containing 1 to 6 sulfur atoms, arylene and alkylarylene. In the case where Q is a bond, the

multi-functional silane comprises two trisubstituted silyl groups which are bonded directly to one another. Preferred multi-silyl-acyloxy silane are bis-(triacetoxysilyl)alkane, bis-(triacetoxysilylalkyl)amine and bis-(triacetoxysilylalkyl)tetrasulfide, most preferably bis-(triacetoxysilyl)ethane, bis-(triacetoxysilylpropyl)amine and bis-(triacetoxysilylpropyl)tetrasulfide.

In an especially preferred embodiment, the acyloxy silane utilised in the present invention is vinyltriacetoxysilane.

Acyloxy silanes utilised in the present invention generally dissolve and hydrolyze readily and completely in water to produce organic acids. For example, where an acetoxy silane is used, acetic acid is produced. Unlike the analogous alkoxy silanes commonly utilised in the prior art which produce alcohols upon hydrolysis, the acyloxy silanes utilised in the present invention produce substantially none or small amounts of VOCs depending on the level of non-acyloxy group substitution in the silanes.

Depending on the level of substitution of acyloxy groups in the silanes utilised in the present invention, the pH of the resultant solution can be predetermined and manipulated. Commonly, high degrees of acyloxy group substitution are present, for example  $\approx 100\%$  substitution, and this can result in a pH as low as 1 or 2. At these low levels of pH, the hydrolysed acyloxysilanes tend to condense, therefore reducing their efficacy. It is therefore necessary to add a base to maintain the pH in an optimal range.

Preferably, where a single silyl group-containing silane is used as the acyloxy silane, 3 of the groups attached to the silicon atom of the silyl group are acyloxy groups, preferably methanoyloxy or acetoxy.

Preferably, where a multi-silyl-acyloxy silane is used, 3 of the groups attached to the each silicon atom of each silyl group are acyloxy groups, preferably methanoyloxy or acetoxy.


The pH of the silane mixture is between about 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 and should be maintained. The pH may be adjusted by the addition of one or more basic compounds or addition of acyloxy silane(s).

During preparation of the treatment solution, a pH of above 2, more preferably above 3, most preferably between 4 and 5 should be maintained.

In order to maintain an optimal pH during preparation of the treatment solution, a basic compound is applied to the treatment solution. The identity of the basic compound(s) is not critical but it is highly beneficial to provide a compound which complements the acyloxy silane. "Complements" means that the basic compound aids, or at least does not substantially detract from the formation of the silane coating on the metal substrate or from the coatings effectiveness in improving corrosion resistance and/or adhesion promotion.

To maintain the pH in the preferred range, the acyloxy silane and the basic compound are preferably mixed together prior to the addition of water and subsequently dissolved in water. Exemplary basic compounds include the carbonates, hydrogen carbonates and hydroxides of the alkali and alkaline earth metals, organic amines, ammonia, amides and the like. A mixture of different basic compounds may be added to the treatment composition.

In a preferred embodiment, the basic compound is a basic silane compound. For example, amino silanes are particularly preferred. In one embodiment, amino silanes which may be employed in the present invention each have a single trisubstituted silyl group in addition to the basic amine moiety, wherein at least one of the substituents is an alkoxy group. Thus, the amino silanes which may be used in the present invention have the general structure



$\text{R}^2$  is chosen from the group consisting of hydrogen and  $\text{C}_1$ - $\text{C}_{24}$  alkyl, preferably  $\text{C}_1$ - $\text{C}_6$  alkyl and each  $\text{R}^2$  may be the same or different. Preferably  $\text{R}^2$  is individually chosen from the group consisting of hydrogen, ethyl, methyl, propyl, iso-propyl, butyl, iso-butyl, sec-butyl and ter-butyl.


X<sup>1</sup> is a group selected from the group consisting of a bond, a substituted or unsubstituted aliphatic or aromatic group. Preferably X<sup>1</sup> is selected from the group consisting of a bond, C<sub>1</sub>-C<sub>6</sub> alkylene, C<sub>2</sub>-C<sub>6</sub> alkenylene, C<sub>1</sub>-C<sub>6</sub> alkylene substituted with at least one amino group, C<sub>2</sub>-C<sub>6</sub> alkenylene substituted with at least one amino group, C<sub>6</sub>-<sub>18</sub> arylene and C<sub>7</sub>-C<sub>18</sub> alkylarylene;

R<sup>3</sup> is a group individually selected from the group consisting of hydrogen, C<sub>1</sub>-C<sub>6</sub> alkyl, C<sub>2</sub>-C<sub>6</sub> alkenyl, C<sub>1</sub>-C<sub>6</sub> alkyl substituted with at least one amino group, C<sub>2</sub>-C<sub>6</sub> alkenyl substituted with at least one amino group, arylene and alkylarylene.

Preferably R<sup>3</sup> is individually selected from the group consisting of hydrogen, ethyl, methyl, propyl, iso-propyl, butyl, iso-butyl, sec-butyl ter-butyl and acetyl.

Particular preferred amino silanes employed in the method of the present invention are γ-aminopropyltriethoxysilane and γ-aminopropyl trimethoxysilane.

In another embodiment, the amino silane may be a bis-silyl aminosilane(s). Such a compound comprises an aminosilane having two trisubstituted silyl groups, wherein the substituents are individually selected from the group consisting of hydroxy and alkoxy. Preferably, the bis-silyl aminosilane comprises:



wherein each R<sup>4</sup> is individually selected from the group consisting of: hydrogen and C<sub>1</sub> - C<sub>24</sub> alkyl;

each R<sup>5</sup> is individually selected from the group consisting of: substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups, and unsubstituted aromatic groups; and

X<sup>2</sup> is either:




wherein each R<sup>6</sup> is individually selected from the group consisting of: hydrogen, substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups; and


R<sup>7</sup> is selected from the group consisting of: substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups

Particularly preferred bis-silyl aminosilanes which may be used in the present invention include:


*bis*-(trimethoxysilylpropyl)amine (which is sold under the tradename A-1170 by Witco):



*bis*-(triethoxysilylpropyl)amine:



and *bis*-(triethoxysilylpropyl)ethylene diamine:



Particularly preferred combinations of acyloxy silanes and basic compounds are:

vinyltriacetoxysilane and *bis*-(trimethoxysilylpropyl)amine;

1,2-*bis*-(triethoxysilyl)ethane and *bis*-(trimethoxysilylpropyl)amine;

vinyltriacetoxysilane and aminopropyltriethoxysilane;

vinyltriacetoxysilane and *bis*-(triethoxysilylpropyl)amine;

1,2-*bis*-(triethoxysilyl)ethane and *bis*-(triethoxysilylpropyl)amine;

vinyltriacetoxysilane and aminopropyltrimethoxysilane.

Where basic silanes are used as the basic compound, additional basic compounds may be used, for example, the inorganic bases referred to above.

The solutions and methods of the present invention may be used on a variety of metals, including steel, aluminium, aluminium alloys, zinc, zinc alloys, magnesium, magnesium alloys, copper, copper alloys, tin and tin alloys. In particular, the present method is particularly useful on zinc, zinc alloy, and metals having a zinc-containing coating thereon, as well as aluminium or aluminium containing substrates. For example, the treatment solutions and methods of the present invention are useful in preventing corrosion of steel having a zinc-containing coating, such as: galvanized steel (especially not dipped galvanized steel), GALVALUME® (a 55%-Al/43.4%-Zn/1.6% - Si alloy coated sheet steel manufactured and sold, for example, by Bethlehem Steel Corp), GALFAN® (a 5%-Al/95%-Zn alloy coated sheet steel manufactured and sold by Weirton Steel Corp., of Weirton, WV), galvanneal (annealed hot dipped galvanized steel) and similar types of coated steel. Zinc and zinc alloys are also particularly amenable to application of the treatment solutions and methods of the present invention. Exemplary zinc and zinc alloy materials include: titanium-zinc (zinc which has a very small amount of titanium added thereto), zinc-nickel alloy (typically about 5% to about 13% nickel content), and zinc-cobalt alloy (typically about 1% cobalt).

The solutions of the present invention may be applied to the metal prior to shipment to the end-user, and provide corrosion protection during shipment and storage (including the prevention of wet-storage stain such as white rust). If a paint or other polymer coating is desired, the end user may merely apply the paint or polymer (e.g., such as adhesives, plastics, or rubber coatings) directly on top of the silane coating provided by the present invention. The silane coatings of the present invention not only provide excellent corrosion protection even without paint, but also provide superior adhesion of paint, rubber or other polymer layers. Thus, unlike many of the currently-employed treatment techniques, the silane coatings of the present invention need not be removed prior to painting (or applying other types of polymer coatings such as rubber).



Suitable polymer coatings include various types of paints, adhesives (such as epoxy automotive adhesives), and peroxide-cured rubbers (e.g., peroxide-cured natural, NBR, SBR, nitrile or silicone rubbers). Suitable paints include polyesters, polyurethanes and epoxy-based paints. Plastic coatings are also suitable including acrylic, polyester, polyurethane, polyethylene, polyimide, polyphenylene oxide, polycarbonate, polyamide, epoxy, phenolic, acrylonitrile-butadiene-styrene, and acetal plastics. Thus, not only do the coatings of the present invention prevent corrosion, they may also be employed as primers and/or adhesive coatings for other polymer layers.

The solutions of the present invention do not require the use or addition of silicates.

The compositions may optionally comprise other silane compounds to the acyloxy silanes or the basic silanes disclosed herein.

The treatment solution is aqueous, and may optionally include one or more compatible solvents (such as ethanol, methanol, propanol or isopropanol) although their presence is not normally required. Where an organic solvent is required, ethanol is preferred. Preferably, solutions of the present invention are substantially free of organic solvents and VOCs.

As mentioned above, the silane(s) in the solution of the present invention are at least partially, and preferably are substantially fully hydrolyzed in order to facilitate the bonding of the silanes to the metal surface and to each other. During hydrolysis, the alkoxy groups in the case of the non-acyloxy silanes and the acyloxy in the case of the acyloxy silanes are replaced by hydroxyl groups. Hydrolysis of the silanes may be accomplished, for example, by merely mixing the silanes in water, and optionally including a solvent (such as an alcohol) in order to improve silane solubility and solution stability.

In order to accelerate silane hydrolysis and avoid silane condensation during hydrolysis, the pH may be maintained below about 8, more preferably between about 4 and about 6, and even more preferably between about 4 and about 5.

It should be noted that the various silane concentrations discussed and claimed herein are all defined in terms of the ratio between the amount (by volume) of unhydrolyzed silane(s) employed to prepare the treatment solution (i.e., prior to hydrolyzation), and the total volume of treatment solution components (i.e., acyloxy silanes, basic compound, water, and optional solvents. In the case of acyloxy silane(s), the concentrations herein (unless otherwise specified) refer to the total amount of unhydrolyzed acyloxy silanes employed, since multiple acyloxy silanes may optionally be present. The basic compounds concentrations herein are defined in the same manner.

As for the concentration of hydrolyzed silanes in the treatment solution, beneficial results will be obtained over a wide range of silane concentrations and ratios. It is preferred, however, that the solution have at least about 0.1% acyloxy silanes by volume, more preferably at least about 1% acyloxy silanes by volume, most preferably between about 2% and about 5% by volume. Lower vinyl silane concentrations generally provide less corrosion protection. Higher concentrations of acyloxy silanes (greater than about 10%) should also be avoided for economic reasons, and to avoid silane condensation (which may limit storage stability).

The concentration of the basic compound required in the treatment solution varies strongly with the type of acyloxy silane employed and the type of basic compound. Obviously, a strongly acidic solution produced by a highly acyloxy group-substituted acyloxy silane will require an appropriate amount of basic compound to result in a treatment solution with a pH in the pre-determined range. Once the pH of the acyloxy silane in solution is known, an appropriate amount of a basic compound (with a known pH value in solution) can be added to the solution. The relative acidity and basicity of the acyloxy silane and the basic compound may be established before the solution is made up and are commonly presented in standard tables reciting physical properties of known compounds. However, the concentration of the basic compound is generally in the range of about 0.1% and about 10% by volume.

Where a basic silane is used as the basic compound, the solution should have at least about 0.1% basic silanes by volume, more preferably at least about 1% basic silane by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

5 As for the ratio of acyloxy silanes to basic compound, a wide range of ratios may be employed, and the present invention is not limited to any particular range of silane ratios.

The mixture of the acyloxy and basic compound may be provided to the user in a pre-mixed, unhydrolysed form which improves shelf life as  
10 condensation of the silane is limited. Such a mixture can then be made up into a treatment solution as defined herein. Such a pre-mixed, unhydrolysed compositions should preferably be substantially free of water but may include one or more organic solvents (such as alcohols). The composition may also include other components such as stabilizers, pigments, desiccants, and the like.

15 Such a pre-mixed composition can be made up with a pre-determined amount of acyloxy silane and basic compound so that the addition of the mixture to water results in a pH within the preferred range. Such pre-mixing prevents or limits a drop in pH, due to the acyloxy silane alone being present in solution, to levels which promote condensation of the silanes in solution. However, the  
20 composition can be presented in a "two-pack" kit, wherein one part of the kit comprises the acyloxy silane, while another part of the kit provides the basic compound.

In either of the above presentation embodiments, the acyloxy silane and basic compound, along with the other components of the composition are  
25 provided in a concentrated form as a powder or liquid mixture. In either case, the concentrate is substantially free of water and may be presented in a hermetically sealed container or kit. Preferably, substantially no organic solvent is present in the composition.

The concentration of the acyloxy silane and basic compound in the pre-  
30 mixed concentrate composition is generally in the range 10-100%, preferably 15-80%, most preferably 25-70%. The concentrate may contain numerous

additional components such as stabilisers, pigments, anti-oxidants, basic pH adjusters, desiccants, adhesion promoters, corrosion inhibitors and the like.

The treatment method itself is very simple. Where the solution is to be made up of separately presented components, the unhydrolyzed acyloxy silane, water, basic compound, solvent (if desired), are combined with one another. The solution is then stirred at room temperature in order to hydrolyze the silanes. The solution generally goes clear when hydrolysis is complete. In this embodiment it is beneficial to maintain the pH of the solution above 2 to limit any condensation of the silanes in solution, particularly the acyloxy silanes.

Where the composition is presented as a pre-mixed kit, the composition is simply added to a pre-determined amount of water and mixed until the solution is substantially clear.

The metal surface to be coated with the solution of the present invention may be solvent and/or alkaline cleaned by techniques well-known to those skilled in the art prior to application of the treatment solution of the present invention. The silane solution is then applied to the metal surface (i.e., the sheet is coated with the silane solution) by, for example, dipping the metal into the solution (also referred to as "rinsing"), spraying the solution onto the surface of the metal, or even brushing or wiping the solution onto the metal surface. Various other application techniques well-known to those skilled in the art may also be used. When the preferred application method of dipping is employed, the duration of dipping is not critical, as it generally does not significantly affect the resulting film thickness. It is merely preferred that whatever application method is used, the contact time should be sufficient to ensure complete coating of the metal. For most methods of application, a contact time of at least about 2 seconds, and more preferably at least about 5 seconds, will help to ensure complete coating of the metal.

As the treatment solution is used up, the acyloxy silane concentration is reduced and the acetic acid concentration remains approximately constant as long as no further acyloxy silane is added to the solution. As further acyloxy silane is added to maintain their concentration, acetic acid is built up in the

solution. To maintain the pH in the preferred range pH adjusters may be added such as basic compounds as hereinbefore described, buffers and the like. In one embodiment, a basic compound may be added along with the additional acyloxy silane which forms a salt with the acid in solution. This may form an insoluble salt which can be removed from the process.

The treatment solution may also be heated when applying the treatment solution. Where the treatment solution is heated, the temperature of the treatment solution is generally in the range 20°C to 80°C, preferably 30°C to 50°C.

After coating with the treatment solution of the present invention, the metal sheet may be air-dried at room temperature, or, more preferably, placed into an oven for heat drying. Preferable heated drying conditions include temperatures between about 20°C and about 200 °C with drying times of between about 30 seconds and about 60 minutes (higher temperatures allow for shorter drying times) More preferably, heated drying is performed at a temperature of at least about 90°C, for a time sufficient to allow the silane coating to dry. While heated drying is not necessary to achieve satisfactory results, it will reduce the drying time thereby lessening the likelihood of the formation of white rust during drying. Once dried, the treated metal may be shipped to an end-user, or stored for later use.

The examples below demonstrate some of the superior and unexpected results obtained by employing the methods of the present invention.

### Examples

#### **Example 1**

Salt Spray test (SST)(Lakebluff) was carried out on A1170/Vinyltriacetoxysilane (1/1, 5%, natural pH=4) treated AA5005 panels. Alkaline cleaned blank and chromated AA5005 panels were chosen as controls. The treated panels were cured at 100°C for 10 min, and then exposed to SST for 29 days, along with the control panels. Four replicates were made for each treatment. The results are presented in Fig. 1.

1. A1170/VTAS treated panels showed original surface after 29 days of exposure to SST, i.e. no corrosion occurred during testing.
2. The blank panels corroded heavily, while the chromated ones pitted apparently.

#### 5      **Example 2**

Salt Spray test (Lakebluff) was carried out on A1170/VTAS (1.5/1.5%, natural pH=4) treated A12024-T3 panels. Alkaline cleaned blank and chromated A12024-T3 panels were chosen as controls. The treated panels were cured at 100°C for 10 min, and then exposed to SST for 7 days, along with the control panels. Three replicates were made for each treatment. The results are presented in Fig. 2.

3. A1170/VTAS treated panels showed almost original surface after 7 days of exposure to SST, i.e., only slight edge corrosion occurred during testing.
4. The blank panels corroded heavily, while the chromated ones pitted slightly.

#### 15      **Example 3**

In order to investigate the paintability of A1170/VTAS water-based silane film on metal substrates, A1170/VTAS (1.5/1.2%, pH=5) water-based silane film was applied on A12023-T3 and HDG, respectively. The treated panels were then powder-painted at Lakebluff with Polyester and Polyurethane powder paints. After that, the panels were put into salt spray chamber for some times, along with the control panels, the blank and the chromated. Three replicates were made for each treatment. The results are shown in Fig. 3.

1. As for A12024-T3 painted with both powder paints (1000hrs in SST), the corrosion performance and paint adhesion improved significantly, which was equal to the chromated and much better than the blank.
2. As for powder-painted HDG (336 hrs in SST), the corrosion performance improved apparently, compared with the chromated

and the blank. The paint adhesion improved somewhat, which was better than the control panels.

**Claims**

1. A method of treating a metal surface, comprising the steps of:
  - (a) providing a metal substrate; and
  - (b) applying a solution to said metal substrate, said solution comprising
    - (iii) at least one acyloxy silane which comprises at least one acyloxy group, wherein said silane has been at least partially hydrolysed; and
    - (iv) at least one basic compound;


wherein the acyloxy silane and the basic compound are present in concentrations to provide a solution pH of between about 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 and wherein the solution is substantially free of acid other than acid produced upon hydrolysis of the acyloxy silane.
2. The method according to claim 1, wherein the metal surface selected from the group consisting of steel, aluminium, aluminium alloys, zinc, zinc alloys, magnesium, magnesium alloys, copper, copper alloys, tin, and, tin alloys.
3. The method according to claim 1, wherein the metal surface is selected from the group consisting of:
  - a metal surface having a zinc-containing coating;
  - zinc;
  - zinc alloy.
  - Aluminium;
  - Aluminium alloy; and
  - steel.
4. The method according to any preceding claim, wherein the acyloxysilane



comprises a single tetrasubstituted silicon atom, wherein the substituents are individually selected from the group consisting of alkyl, alkenyl, alkynyl, aryl, alkaryl, aralkyl, vinyl, amino, ureido, glycidoxy, epoxy, hydroxy, alkoxy, aryloxy and acyloxy, or any of the group alkyl, alkenyl, alkynyl, aryl, alkaryl and aralkyl substituted by a group selected from the group consisting of vinyl, amine, ureido, glycidoxy, epoxy, hydroxy and alkoxy, with the proviso that at least one of the substituents on the silicon atom is an acyloxy group

5. The method according to any preceding claim, wherein the acyloxy groups are preferably all the same and are selected from the group consisting of C<sub>2-12</sub> alkanoyloxy, C<sub>3-12</sub> alkenoyloxy, C<sub>3-12</sub> alkynoyloxy and C<sub>7-18</sub> arenoyloxy, preferably C<sub>2-6</sub> alkanoyloxy, C<sub>3-6</sub> alkenoyloxy, C<sub>3-6</sub> alkynoyloxy and C<sub>7-12</sub> arenoyloxy, preferably ethanoyloxy or methanoyloxy groups.

6. The method according to any preceding claim, wherein the acyloxy silane is selected from the group




wherein W, X, Y and Z are selected from the group consisting of a C-Si bond, substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups and unsubstituted aromatic groups; and R is selected from methyl, ethyl and propyl, preferably ethyl.

7. The method according to claim 1, wherein the acyloxy silane comprises more than one silyl group, preferably two silyl groups.

8. The method according to claim 7, wherein the acyloxy groups are the same and are selected from the group consisting of C<sub>2-12</sub> alkanoyloxy, C<sub>3-12</sub> alkenoyloxy, C<sub>3-12</sub> alkynoyloxy and C<sub>7-18</sub> arenoyloxy, preferably C<sub>2-6</sub> alkanoyloxy, C<sub>3-6</sub> alkenoyloxy, C<sub>3-6</sub> alkynoyloxy and C<sub>7-12</sub> arenoyloxy, preferably ethanoyloxy and methanoyloxy groups.

9. The method according to claim 7 or 8, wherein the acyloxysilane has the structure



wherein Q is selected from the group consisting of either a bond, an aliphatic or aromatic group; and

R<sup>1</sup> is selected from methyl, ethyl and propyl.


10. The method according to claim 9, wherein Q is selected from the group consisting of a bond, C<sub>1</sub>-C<sub>6</sub> alkylene, C<sub>2</sub>-C<sub>6</sub> alkenylene, C<sub>1</sub>-C<sub>6</sub> alkylene substituted with at least one amino group, C<sub>2</sub>-C<sub>6</sub> alkenylene substituted with at least one amino group, C<sub>1</sub>-C<sub>6</sub> alkylene substituted with at least one sulfide group containing 1 to 10 sulfur atoms, C<sub>2</sub>-C<sub>6</sub> alkenylene substituted with at least one sulfide group containing 1 to 10 sulfur atoms, arylene and alkylarylene

11. The method according to claim 10, wherein the acyloxy silane is selected from the group consisting of bis-(triacetoxysilyl)ethane, bis-(triacetoxysilylpropyl)amine and bis-(triacetoxysilylpropyl)tetrasulfide.

12. The method according to claim 1, wherein the acyloxy silane is vinyltriacetoxysilane.

13. The method according to any preceding claim, wherein the basic compound is selected from the carbonates, hydrogen carbonates and hydroxides of the alkali and alkaline earth metals, organic amines, ammonia, amides and silanes, and mixtures thereof.

14. The method according to any preceding claim, wherein the basic compound is a basic silane compound selected from compounds having the general structure



wherein  $R^2$  is chosen from the group consisting of hydrogen and  $C_1$ - $C_{24}$  alkyl, preferably  $C_1$ - $C_6$  alkyl and each R may be the same or different;

$X^1$  is selected from the group consisting of a bond, a substituted or unsubstituted aliphatic or aromatic group; and


$R^3$  is a group individually selected from the group consisting of hydrogen,  $C_1$ - $C_6$  alkyl,  $C_2$ - $C_6$  alkenyl,  $C_1$ - $C_6$  alkyl substituted with at least one amino group,  $C_2$ - $C_6$  alkenyl substituted with at least one amino group, arylene and alkylarylene.

15. The method according to claim 14, wherein  $R^2$  is individually chosen from the group consisting of hydrogen, ethyl, methyl, propyl, iso-propyl, butyl, iso-butyl, sec-butyl and ter-butyl;

$X^1$  is selected from the group chosen from the group consisting of a bond,  $C_1$ - $C_6$  alkylene,  $C_2$ - $C_6$  alkenylene,  $C_1$ - $C_6$  alkylene substituted with at least one amino group,  $C_2$ - $C_6$  alkenylene substituted with at least one amino group, arylene and alkylarylene; and

$R^3$  is individually selected from the group consisting of hydrogen, ethyl, methyl, propyl, iso-propyl, butyl, iso-butyl, sec-butyl ter-butyl and acetyl.


16 The method of any of claims 1 to 13, wherein the basic compound is a bis-silyl aminosilane(s) having the structure



wherein  $\text{R}^4$  is individually selected from the group consisting of: hydrogen and  $\text{C}_1 - \text{C}_{24}$  alkyl;

$\text{R}^5$  is individually selected from the group consisting of: substituted aliphatic groups, unsubstituted aliphatic groups, substituted aromatic groups, and unsubstituted aromatic groups; and

$-\text{X}^2$  is either:



wherein each  $\text{R}^6$  is individually selected from the group consisting of: hydrogen, substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups; and

$\text{R}^7$  is selected from the group consisting of: substituted and unsubstituted aliphatic groups, and substituted and unsubstituted aromatic groups.

17. The method according to claim 1, wherein the basic compounds are selected from the group consisting of  $\gamma$ -aminopropyltriethoxysilane and  $\gamma$ -aminopropyltrimethoxysilane, *bis*-(trimethoxysilylpropyl)amine, *bis*-(triethoxysilylpropyl)amine and *bis*-(triethoxysilylpropyl)ethylene diamine

18. The method according to any preceding claim, wherein a polymer coating is applied to the treated metal substrate.

19. The method of claim 18, wherein the polymer coating is selected from paints, adhesives, rubbers and plastics.

20. The method according to any preceding claim, wherein the solution contains at least about 0.1% acyloxy silanes by volume, more preferably at least about 1% acyloxy silanes by volume, most preferably between about 2% and about 5% by volume.

21. The method according to any preceding claim, wherein the solution contains at least about 0.1% basic compound by volume, more preferably at least about 1% by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

22. A composition comprising an acyloxy silane and a basic compound as defined in any preceding claim, wherein the solution pH is between 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 and wherein the solution is substantially free acids other than acids produced upon hydrolysis of the acyloxy silanes.

23. The composition according to claim 22, wherein the solution contains at least about 0.1% acyloxy silanes by volume, more preferably at least about 1% acyloxy silanes by volume, most preferably between about 2% and about 5% by volume

24. The composition according to claim 22 or 23, wherein the solution contains at least about 0.1% basic compound by volume, more preferably at least about 1% by volume, more preferably between about 2% and about 10%, most preferably between about 2% and about 5% by volume.

25. A composition comprising an acyloxy silane and a basic compound as defined in any of claims 1 to 22, wherein the acyloxy silane is substantially unhydrolysed and the composition is substantially free of water.

26. The composition according to claim 25, wherein the combined concentration of the acyloxy silane and basic compound in composition is generally in the range 10-100%, preferably 15-80%, most preferably 25-70%.

27. The composition according to claim 26, wherein the concentrations of acyloxy silane and basic compound pre-determined so as to provide a solution with a pH in the range of between 3 and about 10, more preferably between about 4 and about 8, most preferably 4 to 5 when dissolved in water.

28. The composition according to any of claims 22 to 27, comprising additional components selected from stabilisers, pigments, anti-oxidants, desiccants, adhesion promoters, corrosion inhibitors and mixtures thereof.

29. A kit comprising a composition according to any of claims 22 to 28.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
25 January 2001 (25.01.2001)

PCT

(10) International Publication Number  
WO 01/06036 A1

(51) International Patent Classification<sup>7</sup>: C23C 22/56,  
22/53, 22/48, 22/68, 22/60

(74) Agents: MARTIN, J., Miller et al.; Dinsmore & Shohl  
LLP, 1900 Chemed Center, 255 East Fifth Street, Cincinnati, OH 45202 (US).

(21) International Application Number: PCT/US00/19646

(22) International Filing Date: 19 July 2000 (19.07.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/356,926 19 July 1999 (19.07.1999) US  
PCT/EP00/06794 17 July 2000 (17.07.2000) EP

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): UNIVERSITY OF CINCINNATI [US/US]; Room G-7, Wherry Hall, Mail Locatoin 0829, Cincinnati, OH 45267 (US).

**Published:**

— With international search report.

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): VAN OOLJ, Wim, J. [NL/US]; 154 Annandale Drive, Fairfield, OH 45014-0012 (US). ZHU, Danqing [CN/US]; 526 Martin Luther King Drive West, Cincinnati, OH 45220 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ACYLOXY SILANE TREATMENTS FOR METALS

(57) Abstract: A method of treating a metal surface by application of a solution containing at least one acyloxy silane and at least one basic compound. A composition having at least one acyloxy silane and at least one basic compound is also provided, along with a silane coated metal surface.

WO 01/06036 A1

10031731 10/031731




Fig.1. A1170/VTAS Mix. Treated AA5005 after 29 days of SST

(a) Blank; (b) Chroamted; (c ) A1170/VTAS treated\*

\* A1170/VTAS: 1.5/1, natural pH=4






Fig. 2. A1170/VTAS Mix. treated Al2024-T3 after 7days of SST

(a) Blank; (b) Chromated; (c) A1170/VTAS treated

\* A1170/VTAS: 1.5/1, 5%, natural pH=4




Fig. 3a Polyester powder painted HDG after 336 hrs of SST

(a) Blank; (b) Chromated; (c) A1170/VTAS treated

\* A1170/VTAS: 1.5/1, 2%, natural pH=5

100031731




Fig. 3b. Polyester powder painted Al2024-T3 after 1000 hrs of SST  
(a) Blank; (b) Chromated; (c) A1170/VTAS treated

\* A1170/VTAS: 1.5/1, 2%, natural pH=5




Fig. 3c Polyurethane powder painted Al2024 after 1000 hrs of SST

(a) Blank; (b) Chromated; (c) A1170/VTAS treated

\* A1170/VTAS: 1.5/1, 2%, natural pH=5

MAY. 20. 2002 2:34PM

DINSMORE SHOHL

NO. 6358

P. 2

002

**DECLARATION**  
**and**  
**POWER OF ATTORNEY**

**U.S. NATIONAL PHASE OF INTERNATIONAL APPLICATION**

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled **ACYLOXY SILANE TREATMENTS FOR METALS**, the specification of which was filed as International Application No. PCT/US00/19646 on July 19, 2000,

- ☐ and was amended under Article 19 on \_\_\_\_\_  
(if applicable)
- ☐ and was amended under Article 34 on \_\_\_\_\_  
(if applicable)
- ☒ and was assigned U.S. Application Serial No. 10/031,731  
and was amended on January 22, 2002  
(if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby claim foreign priority benefits and/or U.S. Provisional application priority benefits under Title 35, United States Code, §119 of any foreign application(s) or U.S. Provisional applications for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior U.S. Provisional or Foreign Application(s)				
			Priority Claimed	
Number	Country	Day/Month/Year Filed	Yes	No

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulation, §1.56(a) which occurred between the filing date of the prior application and the PCT international filing date of this application:

MAY. 20. 2002 2:35PM

DINSMORE SHOHL

NO. 6358

P. 3

09/356,926	19 July 1999	pending
(Application Serial No.)	(Filing Date)	(Status)
		(patented, pending, abandoned)

PCT/EP00/06794	17 July 2000	pending
(Application Serial No.)	(Filing Date)	(Status)
		(patented, pending, abandoned)


13 I hereby appoint Martin J. Miller, Registration No. 35,953; Holly D. Kozlowski, Registration No. 30,468; Ronald J. Snyder, Registration No. 31,062; James D. Liles, Registration No. 28,320; Lynda E. Roesch, Registration No. 29,696; Charles H. Brown, III, Registration No. 48,866; John V. Harmeyer, Registration No. 41,815; Geoffrey L. Oberhaus, Registration No. 42,255; Stephen S. Wentsler, Registration No. 46,403; Ryan O. White, Registration No. 45,541; Rebecca A. Brown, Registration No. 47,452; Clayton L. Kuhnell, Registration No. 48,691; and Jeffrey R. Schaefer, Registration No. 48,514, my attorneys, c/o Dinsmore & Shohl, 1900 Chemed Center, 255 East Fifth Street, Cincinnati, Ohio 45202 (513) 977-8200, with full power in each of them, of substitution and revocation, to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith.

The undersigned hereby authorizes the above-named U.S. attorneys to accept and follow instructions from University of Cincinnati as to any action to be taken in the Patent and Trademark Office regarding this application without direct communication between the undersigned and the aforementioned U.S. attorneys. In the event of a change in the firm or persons from whom instructions may be taken, the aforementioned U.S. attorneys will be so notified in writing by the undersigned.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

\*\*\*\*\*

Full name of sole or first inventor: Wim J. van Ooij

Inventor's signature: 

5/21/02  
Date

Residence: 154 Annandale Drive, Fairfield, OH 45014  
Citizenship: Dutch  
Post Office Address: 154 Annandale Drive, Fairfield, OH 45014

MAY 20. 2002 2:35PM

DINSMORE SHOHL

NO. 6358 P. 4

2-00  
Full name of second inventor: Danqing Zhu

Inventor's signature: Danqing Zhu

5/21/02

Date

Residence: 526 Martin Luther King Drive West, Cincinnati, Ohio 45220  
Apt. #1

Citizenship: Chinese

Post Office Address: 526 Martin Luther King Drive West, Cincinnati, Ohio 45220  
Apt. #1

778889.01